

**JUPITER MINES
LIMITED**

ABN 51 105 991 740

ASX Release

12 February 2008

JUPITER MINES LTD

Suite 2 Level 16
Norwich House
19 Bligh Street
Sydney NSW 2000
Australia
Tel: +61 2 9235 2755
Fax: +61 2 9235 2955

Contact:

Greg Durack
Robert Benussi

Email:

info@jupitermines.com

For the Latest News:

www.jupitermines.com

Directors/Officers

Paul Murray
Alan Topp
William Wang
Patrick Sam Yue

Greg Durack
Robert Benussi
Charles Guy

Issued Capital:

Shares: 141,667,544
Unlisted Opts: 29,750,000

ASX Symbol: JMS

Currently Exploring for:

- Iron Ore
- Nickel
- Uranium
- Gold

Jupiter Mines Limited

**ENCOURAGING INTERSECTIONS OF
IRON ORE FROM BROCKMAN IRON PROJECT**

KEY POINTS

- **Encouraging initial results from RC drilling at Brockman Project including:**
 - 7m @ 59.4% Fe (62.9% CaFe) from surface
 - 7m @ 56.5% Fe (62.8% CaFe) from surface
 - 5m @ 55.7% Fe (60.7% CaFe) from surface
 - 7m @ 56.9% Fe (60.2% CaFe) from surface
 - 9m @ 56.3% Fe (59.0% CaFe) from surface
- **Brockman Project strategically located near Rio Tinto's Brockman 3 Iron Ore Operations and FMG's field camp.**
- **Application lodged for new tenement abutting the Brockman tenements.**
- **Exploration program to be developed for expanded tenement holding.**

Jupiter Mines Limited (ASX: **JMS** – "Jupiter") is pleased to announce that it has received encouraging assay results from the initial drilling program completed at its 100%-owned **Brockman Iron Project**, located 60km west of Tom Price in the Pilbara region of Western Australia.

The Brockman Iron Project is well located with respect to regional mining infrastructure, with the western boundary of the Brockman tenements adjoining Rio Tinto's Brockman 3 Iron Ore Operations and located near Fortescue Metal Group's Pilbara field camp.

Jupiter completed a preliminary 2-week drilling program in November 2007, which was designed to test iron mineralisation detected from previous surface rock chip sampling. The program comprised 33 RC vertical holes totalling 990 metres, which were drilled in a series of seven traverses approximately 200 metres apart, orientated along the dip of the local geology (see Attachment 1).

The best intersection was in hole BRC005, which returned **7 metres @ 59.4% Fe (62.9% calcined Fe or CaFe)**. Jupiter is encouraged with this first pass program with the better intersections summarized below:

Hole No.	From (m)	Width (m)	Fe (%)	LOI (%)	Al ₂ O ₃ (%)	P (%)	S (%)	SiO ₂ (%)	CaFe (%)
BRC001	0	7	51.5	9.87	6.46	0.040	0.025	8.74	56.6
BRC001	8	1	52.3	11.65	6.16	0.034	0.027	6.09	58.4
BRC002	0	2	55.8	4.91	6.22	0.036	0.016	7.53	58.5
BRC002	3	9	52.2	11.55	5.67	0.044	0.030	7.14	58.2
BRC003	0	9	53.6	5.52	6.48	0.030	0.015	8.47	56.6
BRC005	0	7	59.4	6.03	2.43	0.049	0.038	5.88	62.9
BRC013	2	7	50.0	11.3	5.35	0.023	0.013	10.9	55.7
BRC018	0	7	49.6	9.7	6.56	0.029	0.022	11.99	52.1
BRC020	0	9	56.3	4.96	5.87	0.030	0.017	7.37	59.0
BRC021	0	7	56.9	5.83	6.29	0.029	0.037	5.56	60.2
BRC022	0	5	55.7	9.05	3.44	0.042	0.039	7.32	60.7
BRC025	0	7	56.6	10.99	3.11	0.045	0.039	4.21	62.8
BRC032	0	5	49.4	9.45	6.12	0.035	0.043	12.98	54.5
BRC033	2	3	52.6	9.32	7.2	0.028	0.020	6.93	56.8

Notes:

- 1) *Analyses conducted by ALS Chemex using Fusion/XRF analysis with Loss on Ignition (LOI) determined using OA-Grad5t Multi-temperature analyses*
- 2) *Calcined Fe (CaFe) calculated by using the formula $CaFe\% = ((Fe\%) / (100 - LOI\ 1,000)) * 100$*

A full table of sample results from the program is provided in Attachment 3 to this announcement, while drill hole locations are shown in Attachments 1 and 2.

In light of the encouraging results from this preliminary program, Jupiter has lodged an application for Prospecting Licence PLA47/1314, which abuts the Brockman Iron Project tenement. Areas have been identified on this tenement that warrant follow-up exploration through field-based activities including mapping and rock chip sampling.

The Company's broader exploration strategy at the Brockman Iron Project will be reviewed once an initial program of field activities has been completed on the new Prospecting Licence, and in conjunction with its other exploration priorities at its Central Yilgarn Iron Ore Project.

The Brockman Iron Project represents a strategic exploration opportunity for Jupiter within a world-class iron ore mining region.


Greg Durack
Chief Executive Officer

Telephone: (61-8) 9381 9133

Competent Person

The information in this announcement that relates to Exploration Results is based on information compiled by Mr Charles William Guy who is a Member of the Australian Institute of Geoscientists and a full-time employee of Jupiter Mines Limited. Charles William Guy has sufficient experience which is relevant to the style of mineralisation and type of deposit under consideration and to the activity that he is undertaking to qualify as a Competent Person as defined in the 2004 Edition of the 'Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves'. Charles William Guy consents to the inclusion in the announcement of the matters based on his information in the form and context in which it appears

Attachment 1: Brockman Iron Project Drill Hole Location Map



Attachment 2: Drill Hole Locations

Hole No.	Depth	Elev	East	West	Type	dip
BRC001	74	596	7504551	541989	RC	90
BRC002	63	599	7504536	542019	RC	90
BRC003	54	602	7504510	542044	RC	90
BRC004	57	606	7504449	542076	RC	90
BRC005	51	608	7504415	542109	RC	90
BRC006	43	613	7504379	542147	RC	90
BRC007	38	617	7504359	542195	RC	90
BRC008	26	622	7504323	542247	RC	90
BRC009	27	615	7504395	541889	RC	90
BRC010	25	633	7504256	541872	RC	90
BRC011	25	634	7504346	541883	RC	90
BRC012	33	635	7504183	541932	RC	90
BRC013	27	595	7504747	542130	RC	90
BRC014	33	602	7504720	542171	RC	90
BRC015	12	628	7504659	542324	RC	90
BRC016	18	619	7504724	542241	RC	90
BRC017	24	613	7505394	542798	RC	90
BRC018	24	602	7505422	542779	RC	90
BRC019	30	601	7505428	542749	RC	90
BRC020	30	600	7505069	542464	RC	90
BRC021	21	604	7505065	542485	RC	90
BRC022	24	607	7505037	542506	RC	90
BRC023	24	612	7505016	542542	RC	90
BRC024	22	614	7504972	542583	RC	90
BRC025	24	616	7504903	542630	RC	90
BRC026	21	630	7504753	542453	RC	90
BRC027	18	623	7504834	542399	RC	90
BRC028	15	615	7504896	542343	RC	90
BRC029	27	604	7504910	542306	RC	90
BRC030	18	626	7505137	542760	RC	90
BRC031	24	616	7505236	542676	RC	90
BRC032	18	604	7505239	542644	RC	90
BRC033	21	601	7505261	542608	RC	90

Attachment 3: Drill Hole Assay Results

Hole No.	Depth (From)	Depth (To)	SAMPLE DESCRIPTION	Fe (%)	LOI 1000 (%)	Al ₂ O ₃ (%)	P (%)	S (%)	SiO ₂ (%)
BRC001	0	1	349628	48.1	4.86	5.35	0.054	0.023	19.65
	1	2	349629	49.1	8.34	8.11	0.047	0.02	11.8
	2	3	349630	51.9	9.83	7.48	0.036	0.026	7.25
	3	4	349631	53.2	11	5.45	0.041	0.035	6.31
	4	5	349632	50.9	12.15	7.62	0.04	0.027	6.09
	5	6	349633	54.5	11.65	5	0.033	0.021	4.5
	6	7	349634	53	11.25	6.21	0.029	0.024	5.56
	7	8	349635						
	8	9	349636	52.3	11.65	6.16	0.034	0.027	6.09
	9	10	349638	51.6	11.65	4.81	0.031	0.034	8.84
BRC002	0	1	82910	56.1	4.79	6.09	0.037	0.017	7.35
	1	2	82911	55.4	5.13	6.36	0.034	0.015	7.72
	2	3	82912						
	3	4	82913	54.2	9.92	6.39	0.037	0.033	4.92
	4	5	82914	54.2	11.1	5.68	0.055	0.037	3.98
	5	6	82915	53.6	12.35	5.4	0.048	0.041	4.35
	6	7	82916	52.8	12.7	5.77	0.036	0.032	4.89
	7	8	82918	52.1	12.25	5.93	0.031	0.03	6.35
	8	9	82919	51.9	12.25	5.9	0.032	0.032	6.78
	9	10	82920	51	11.85	4.52	0.034	0.024	9.95
	10	11	82921	49.5	11.05	5.82	0.05	0.021	11.75
	11	12	82922	50.3	10.5	5.63	0.07	0.023	11.3
	12	13	82923	43.1	7.13	3.53	0.051	0.014	27.2
	13	14	82924	34.4	3.51	1.08	0.032	0.007	45.9
	14	15	82925	23.4	2.6	1.5	0.022	0.007	62.1
BRC003	0	1	82980	55	4.19	5.39	0.045	0.02	10.35
	1	2	82981	55.9	4.97	6.01	0.033	0.016	7.43
	2	3	82982	58	4.43	5.44	0.032	0.015	5.58
	3	4	82983	56.5	4.58	6.11	0.03	0.014	6.49
	4	5	82984	53.2	5.52	7.46	0.027	0.014	8.34
	5	6	82985	51.4	5.71	7.72	0.026	0.012	9.45
	6	7	82986	53.1	5.98	6.85	0.028	0.009	6.83
	7	8	82988	50	7.07	6.99	0.025	0.016	10.15
	8	9	82989	49.4	7.31	6.41	0.024	0.013	11.6
	9	10	82990	43.2	12.15	5.22	0.022	0.019	14.95
	10	11	82991	38.6	11.3	4.98	0.014	0.024	23.1
	11	12	82992	48.8	11.9	3.43	0.022	0.037	12.75
	12	13	82993	9.13	4.22	4.04	0.007	0.018	>70
	13	14	82994	24.1	5.86	2.96	0.021	0.016	55.8
BRC004	0	1	83040	53.9	6.21	5.99	0.03	0.038	9.04
	1	2	83041	55.3	6.22	5.02	0.034	0.048	8.14
	2	3	83042						
	3	4	83043	59.7	7.93	2.01	0.041	0.032	3.93
	4	5	83044	60.8	6.32	1.62	0.042	0.032	4.7
	5	6	83045	61.4	5.83	1.74	0.044	0.03	4.23
	6	7	83046	61.4	5.88	1.12	0.068	0.027	4.8
	7	8	83051	59.6	7.16	1.3	0.072	0.026	5.84
	8	9	83052	54.3	9.96	2.88	0.077	0.035	8.81
	9	10	83053	55	7.56	2.76	0.06	0.043	10.35

Hole No.	Depth (From)	Depth (To)	SAMPLE DESCRIPTION	Fe (%)	LOI 1000 (%)	Al ₂ O ₃ (%)	P (%)	S (%)	SiO ₂ (%)
BRC005	0	1	83106	54.4	10.85	4.16	0.04	0.038	6.06
	1	2	83108	58.7	5.28	3.97	0.041	0.051	5.59
	2	3	83109	61.7	6.16	2.02	0.04	0.041	3.04
	3	4	83110	61.8	5.24	2.7	0.053	0.041	2.95
	4	5	83111	61	4.71	1.67	0.063	0.038	5.81
	5	6	83112	60	4.71	1.4	0.061	0.033	7.58
	6	7	83113	58.1	5.28	1.06	0.046	0.024	10.1
	7	8	83114	53	7.06	2.64	0.053	0.03	13.75
	8	9	83115	50.4	9	3.99	0.047	0.032	14.2
	9	10	83116	50.5	7.95	4.64	0.054	0.039	14.15
	10	11	83118	46.8	8.5	5.6	0.045	0.041	17.75
	11	12	83119	40.3	8.22	4.25	0.033	0.073	27.8
	12	13	83120	52.2	9.96	4.48	0.051	0.06	10.15
	13	14	83121	52.9	9.89	4.47	0.049	0.048	9.34
14	15	83122	50.3	10.85	6.48	0.033	0.035	9.96	
BRC006	0	1	83163	50.9	7.59	7.76	0.041	0.032	10.6
	1	2	83164	39.9	8.27	5.19	0.033	0.038	26.4
	2	3	83165	56.5	11.2	4.01	0.048	0.05	3.14
	3	4	83166	57.1	8.2	5.3	0.048	0.038	3.65
	4	5	83167	57.4	7.75	5.17	0.047	0.035	3.77
	5	6	83169	53.4	10.75	7.92	0.04	0.04	4.05
	6	7	83170	50.1	11.75	8.65	0.025	0.045	7.15
	7	8	83171	47.2	8.94	5.76	0.024	0.037	17.15
	8	9	83172	31.3	6.63	3.53	0.014	0.025	44.3
	9	10	83173	26.3	4.41	1.58	0.006	0.026	55.9
	10	11	83174	26.4	4.34	1.62	0.006	0.028	55.8
11	12	83175	28.1	3.5	1.22	0.005	0.024	54.6	
BRC007	0	1	83214	37.4	7.51	3.69	0.039	0.036	33.7
	1	2	83215	42.9	7.51	3.49	0.038	0.047	26.3
	2	3	83216	41.6	7.78	4.02	0.033	0.049	27.3
	3	4	83218	16.95	4.16	2.75	0.012	0.025	68.1
	4	5	83219	24.8	5.91	3.08	0.013	0.051	54.6
BRC008	0	1	83254	32.7	4.01	2.29	0.029	0.03	45.7
	1	2	83255	22.5	3.58	1.87	0.02	0.033	61.2
	2	3	83256	28	4.99	1.83	0.03	0.034	51.9
BRC009	0	1	83283	56	6.41	3.64	0.051	0.038	9.16
	1	2	83284	46.2	4.38	2.05	0.042	0.057	26.8
	2	3	83285	37.9	5.08	2.24	0.039	0.069	37.8
BRC010	0	1	83341	30.3	3.47	4.54	0.027	0.033	47.8
	1	2	83342	19.25	3.42	2.48	0.015	0.031	65.7
	2	3	83343	23	3.65	2.58	0.013	0.032	60.1
BRC011	0	1	83313	43.4	6.45	5.4	0.042	0.042	25
	1	2	83314	36.5	6.67	6.12	0.034	0.05	34.2
	2	3	83315	47.7	6.06	3.45	0.031	0.046	21.7
	3	4	83316	49.2	7.68	3.94	0.031	0.062	17.45
	4	5	83318	49.8	7.97	3.79	0.048	0.048	16.15
	5	6	83319	55.2	7.1	2.26	0.042	0.04	11.3
	6	7	83320	56.8	6.98	1.94	0.038	0.033	9.42
	7	8	83321	57.4	7.02	1.93	0.045	0.035	8.61

Hole No.	Depth (From)	Depth (To)	SAMPLE DESCRIPTION	Fe (%)	LOI 1000 (%)	Al ₂ O ₃ (%)	P (%)	S (%)	SiO ₂ (%)
BRC012	0	1	83369	44.2	7.77	3.51	0.071	0.046	24.4
	1	2	83370	39.6	7.12	3.36	0.057	0.035	32
	2	3	83371	37.3	6.27	2.35	0.054	0.036	37.3
	3	4	83372	30.4	6.52	1.41	0.056	0.029	47
	4	5	83373	31.4	6.22	1.42	0.046	0.034	46
	5	6	83374	28.7	5.01	2	0.039	0.032	50.8
BRC013	0	1	83405	36.2	6.66	5.19	0.022	0.036	35.1
	1	2	83406	42.9	9.79	6.64	0.021	0.029	21.2
	2	3	83408	47.3	10.45	7.25	0.024	0.021	13.6
	3	4	83409	49.5	11.6	6.08	0.022	0.017	10.45
	4	5	83410	51.4	11.45	5.39	0.023	0.011	8.72
	5	6	83411	51.6	11.8	5.15	0.026	0.01	8.51
	6	7	83412	51.3	11.55	4.8	0.022	0.011	9.47
	7	8	83413	51.6	11.4	4.68	0.021	0.01	9.34
	8	9	83414	47.6	10.65	4.12	0.021	0.011	16.5
	9	10	83415	28.6	7.19	4.34	0.013	0.013	46.8
BRC014	10	11	83416	18.9	5.1	4.73	0.01	0.005	62.3
	0	1	83435	51.2	9.7	6.34	0.038	0.029	9.99
	1	2	83436	35	6.53	2.77	0.025	0.016	40.1
	2	3	83438	28.9	5.44	2.49	0.02	0.017	50.1
	3	4	83439	48.7	8.84	5.12	0.033	0.058	15.5
	4	5	83440	43.4	8.14	4.25	0.024	0.047	24.6
	5	6	83441	45.2	9.46	4.75	0.024	0.042	20.5
BRC016	6	7	83442	36.5	7.58	3.77	0.02	0.033	35.9
	0	1	83485	37	5.99	4.33	0.029	0.025	36
BRC017	1	2	83486	29.7	3.61	1.76	0.023	0.01	51.5
	0	1	83505	50.6	8.14	6.25	0.045	0.027	12.2
	1	2	83506	42.8	9.25	6.5	0.036	0.04	22.2
	2	3	83508	45.2	9.65	6.49	0.034	0.038	18.3
	3	4	83509	29.4	10.8	2.92	0.027	0.03	43.4
	4	5	83510	37.5	6.37	4.29	0.044	0.031	34.1
	5	6	83511	35.9	4.89	3.77	0.032	0.032	38.9
	6	7	83512	26	4.3	2.96	0.016	0.023	54.9
BRC018	7	8	83513	26.4	3.93	2.19	0.017	0.023	55.6
	0	1	83533	50	8.71	7.71	0.04	0.017	11.05
	1	2	83534	51	9.61	7.62	0.037	0.02	8.83
	2	3	83535	51.1	9.37	7.04	0.032	0.021	9.62
	3	4	83536	48.4	10.2	5.98	0.021	0.027	13.75
	4	5	83538	50.3	9.99	5.81	0.024	0.026	11.6
	5	6	83539	49.9	9.76	5.68	0.026	0.021	12.45
	6	7	83540	46.3	10.3	6.08	0.025	0.024	16.65
	7	83541	33.9	7.7	4.26	0.027	0.015	38.9	

Hole No.	Depth (From)	Depth (To)	SAMPLE DESCRIPTION	Fe (%)	LOI 1000 (%)	Al ₂ O ₃ (%)	P (%)	S (%)	SiO ₂ (%)
BRC019	0	1	83551	51.8	8.6	7.46	0.029	0.016	8.36
	1	2	83552	49.4	10.1	7.75	0.021	0.019	9.62
	2	3	83553	49.4	10.25	7.66	0.023	0.019	9.49
	3	4	83554	48.6	11.15	8.01	0.021	0.023	8.9
	4	5	83555	40.7	9.4	6.7	0.015	0.022	24
	5	6	83556	41.7	9.71	5.24	0.02	0.013	24.1
	6	7	83558	39	9.37	4.99	0.017	0.013	28.3
	7	8	83559	42.2	9.99	5.34	0.017	0.028	22.9
	8	9	83560	41.5	10.2	5.06	0.018	0.029	23.8
	9	10	83561	44.4	10.65	4.03	0.015	0.033	20.1
	10	11	83562	35.6	9.16	4.52	0.013	0.028	33.8
BRC020	0	1	83573	52.8	5.8	6.24	0.04	0.017	11
	1	2	83574	53	6.1	6.31	0.032	0.016	10.6
	2	3	83575	58.2	4.49	4.84	0.029	0.017	6.4
	3	4	83576	57.8	6.04	5.52	0.029	0.014	4.74
	4	5	83578	58.9	4.55	5.46	0.025	0.017	4.68
	5	6	83579	55.4	4.04	6.98	0.026	0.02	8.12
	6	7	83580	56.5	3.87	6.77	0.028	0.02	7.17
	7	8	83581	60	2.75	5.53	0.031	0.019	4.29
	8	9	83582	53.9	7.03	5.19	0.035	0.015	9.36
	9	10	83583	45.5	8.24	4.17	0.026	0.011	21.3
	10	11	83584	46.9	8.83	4.15	0.025	0.018	18.55
	12	13	83585	49.3	11	3.96	0.015	0.043	13.4
	14	15	83586	48.5	11.45	5.25	0.024	0.042	12.85
	BRC021	0	1	83594	57.3	6.01	5.88	0.027	0.018
1		2	83595	56.6	5.77	6.04	0.027	0.02	6.12
2		3	83596	58.9	5.07	5.68	0.026	0.023	3.9
3		4	83598	56.6	6.7	6.98	0.028	0.062	4.48
4		5	83599	57.8	5.51	5.66	0.032	0.043	5.32
5		6	83600	57.6	5.48	5.64	0.034	0.043	5.7
6		7	83601	53.3	6.31	8.18	0.034	0.05	8.41
7		8	83602	50.1	8.75	8.69	0.03	0.052	10.15
8		9	83603	44.6	10.6	10.6	0.045	0.029	14.1
10		11	83604	52.7	10.45	4.31	0.063	0.018	9.18
12		13	83605	51.1	10.25	3.68	0.065	0.021	12.4
14	15	83606	54	10.7	3.57	0.044	0.025	7.86	
BRC022	0	1	83611	54.5	9.17	5.07	0.058	0.033	7.2
	1	2	83612	56.5	10.15	4.46	0.046	0.033	3.93
	2	3	83613	57.5	8.82	3.6	0.042	0.037	4.81
	3	4	83614	55.4	8.72	2.29	0.038	0.049	9.34
	4	5	83615	54.6	8.39	1.76	0.027	0.032	11.3

Hole No.	Depth (From)	Depth (To)	SAMPLE DESCRIPTION	Fe (%)	LOI 1000 (%)	Al ₂ O ₃ (%)	P (%)	S (%)	SiO ₂ (%)
BRC023	0	1	83626	40.3	6.4	4.57	0.043	0.016	30.5
	4	5	83628	36.2	5.5	1.5	0.044	0.029	40.8
BRC024	0	1	83639	42.6	8.39	5.69	0.054	0.02	24.1
	1	2	83640	48.6	7.85	2	0.046	0.022	20.1
	2	3	83641	48.5	7.89	2.05	0.045	0.022	20.2
	3	4	83642	53.9	9.22	1.22	0.096	0.019	12
	4	5	83643	48.9	8.64	2.1	0.072	0.02	18.65
	6	7	83644	46.3	9.89	2.72	0.061	0.022	20.6
BRC025	0	1	83653	56.1	9.45	4.29	0.056	0.034	4.99
	1	2	83654	54	9.47	3.13	0.055	0.034	9.12
	2	3	83655	56.8	12.2	3.25	0.048	0.041	2.37
	3	4	83656	56.9	11.7	3.23	0.037	0.035	3.16
	4	5	83658	57.6	11.55	2.92	0.037	0.043	2.77
	5	6	83659	58.1	11.55	2.69	0.038	0.039	2.19
	6	7	83660	56.8	11.05	2.27	0.046	0.045	4.88
BRC026	0	1	83670	26.3	4.33	1.42	0.021	0.009	56.2
	1	2	83671	24.4	3.12	0.48	0.02	0.01	61.1
BRC027	0	1	83682	27.9	4.89	2.31	0.041	0.031	52.2
	1	2	83683	26.8	3.36	1.44	0.021	0.024	56.6
BRC028	0	1	83693	37.6	5.71	3.75	0.03	0.015	36
	1	2	83694	34	5.37	2.22	0.027	0.021	43.6
	3	4	83695	28.3	5.26	3.52	0.03	0.025	50.5
BRC029	0	1	83701	47.2	8.54	5.78	0.039	0.046	17.35
	1	2	83702	44.7	7.55	4.43	0.041	0.071	23.5
	2	3	83703	46.4	7.89	4.68	0.042	0.078	20.5
	3	4	83704	46.4	6.35	3.94	0.024	0.064	22.9
	4	5	83705	49	7.6	3.57	0.037	0.065	18.35
	6	7	83706	42.8	7.05	7.01	0.029	0.04	24.4
	8	9	83708	33.8	5.36	3.52	0.023	0.031	42.4
	BRC030	0	1	83719	27.2	3.43	1.98	0.018	0.019
1		2	83720	27.8	2.88	1.04	0.017	0.041	56
BRC031	0	1	83729	47	8.4	7.99	0.035	0.035	15.2
	1	2	83730	39.5	9.31	6.62	0.023	0.027	26.5
	2	3	83731	35	8.56	6.07	0.025	0.021	34.3
	3	4	83732	39.9	8.7	4.69	0.027	0.02	28.7
	4	5	83733	32.8	8.06	4.6	0.022	0.014	39.6
	6	7	83734	24.5	4.95	2.27	0.033	0.008	57.3
	8	9	83735	26.8	3.24	0.91	0.026	0.013	57.2
	10	11	83736	26.9	3.23	1.18	0.008	0.02	56.9
BRC032	0	1	83744	49.6	8.65	7.57	0.04	0.031	11.9
	1	2	83745	51.1	10.3	5.56	0.032	0.052	10.4
	2	3	83746	51.8	9.82	6.04	0.033	0.042	9.32
	3	4	83748	47.4	9.09	6.05	0.041	0.051	16.3
	4	5	83749	47.1	9.47	5.37	0.031	0.041	17
	5	6	83750	45	8.75	3.72	0.033	0.023	22.8
	6	7	83751	36	6.68	3.27	0.038	0.028	38.2
BRC033	0	1	83758	39.7	9.03	9.09	0.031	0.018	23.4
	1	2	83759	44.6	9.78	9.88	0.03	0.018	14.45

2	3	83760	56.1	7.27	5.52	0.031	0.019	4.99
3	4	83761	50.5	9.44	8.12	0.03	0.026	7.52
4	5	83762	49.4	11.25	7.96	0.024	0.016	8.28
5	6	83763	43.7	11.25	8.48	0.026	0.014	16.25
6	7	83764	39	9.01	5.08	0.023	0.013	29
7	8	83765	39.2	9.29	4.11	0.022	0.02	29.9
8	9	83766	36.6	8.16	2.71	0.023	0.026	36.1
10	11	83768	37.1	8.31	3.68	0.022	0.024	34.4

ENDS